



**PARAMETERS OF ROTOCURED
RUBBER SHEETING**

Item	Colour	Rubber base	Appliance	Strength (MPa)	Elongation (%)	Hardness (ShA)	Temperature range (°C)	Density (g/cm ³)
7993	black	SBR	universal use	4	200	65	-25 / +80	1,47
7994	black	SBR		4	400	50	-25 / +80	1,50
7759	black	SBR		4	100	80	-25 / +80	1,55
9035	white	SBR		6	400	65	-25 / +70	1,51
7665	grey	SBR		6	400	65	-25 / +70	1,53
7667	green	SBR		6	400	65	-25 / +70	1,53
7668	blue	SBR		6	400	65	-25 / +70	1,53
7669	red	SBR		6	400	65	-25 / +70	1,53
7749	black	SBR	mech. stress	10	300	70	-25 / +80	1,19
7645	black	NBR-SBR	oilproof	3	200	65	-25 / +80	1,65
7672	black	NBR-SBR		8	250	70	-25 / +80	1,30
7815	black	EPDM	heat resistant	10	400	60	-40 / +125	1,22
7911	black	EPDM		12	400	60	-40 / +125	1,14
7795	black	EPDM		7	250	70	-40 / +100	1,33
7796	black	EPDM		7	250	80	-40 / +100	1,33
7659	black	EPDM-NR		12	650	65	-40 / +125	1,15
7661	orange	EPDM-NR		12	650	65	-40 / +125	1,15
7816	white	EPDM-NR	food grade	6	400	60	-40 / +125	1,27
7689	grey	NR	PARA quality	12	600	40	-25 / +70	1,00
7742	brown	NR		12	500	40	-25 / +70	< 1,00
7750	black	NR-SBR-BR	wear resistant	17	400	60	-25 / +70	1,15
7987	black	CR-SBR	universal use	8	300	65	-25 / +80	1,40
7887	black	CR-SBR		6	300	50	-25 / +80	1,30
9001	brown	CR-NR	soundproof	3	100	65	-25 / +80	2,44